



Product Data Sheet

■ FX™-120HS

Carthage Mills’ FX™-120HS is a multipurpose nonwoven geotextile of 100% polypropylene staple fibers that have been needlepunched and heatset.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> Mechanical			
Grab Tensile	ASTM D 4632	1335 N	300 lbs
Grab Tensile Elongation		50%	
Wide Width Tensile	ASTM D 4595	18.3 kN/m	105 lbs/in
Mullen Burst	ASTM D 3786	3995 kPa	580 psi
Puncture	ASTM D 4833	775 N	175 lbs
Trapezoidal Tear	ASTM D 4533	510 N	115 lbs
<input type="checkbox"/> Endurance			
UV Resistance	ASTM D 4355	70% @ 500 hrs	
<input type="checkbox"/> Hydraulics / Filtration			
Apparent Opening Size (AOS)	ASTM D 4751	0.150 mm	100 US Std. Sieve
Percent Open Area	CW-02215	0%	
Permittivity	ASTM D 4491	1.00 sec ⁻¹	
Permeability		0.29 cm/sec	
Flow Rate		3055 l/min/m ²	75 gpm/ft ²
<input type="checkbox"/> Physical / Dimensional			
Mass Per Unit Area (Typical)	ASTM D 5261	406.8 g/m ²	12.0 oz/yd ²
Thickness (Typical)	ASTM D 5199	3.05 mm	120 mils
Standard Roll Sizes / Packaging (Special sizes, packaging and fabrication are available.)	Measured (Typical)	4.57 m x 91.5 m 418 m ² 181.4 kg 54.6-63.5 cm diam.	15.0 ft x 300 ft 500 yd ² 400 lbs 21.5-25 in. diameter

Unless otherwise noted, all properties reported are Minimum Average Roll Values (MARV), and are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any sample taken during quality assurance testing will exceed the value reported.

The properties reported above are effective 02/01/03 and are subject to change without notice.

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein. Any implied warranty of fitness for a particular purpose is expressly excluded, and, to the extent that it is contrary to the foregoing sentence, any implied warranty of merchantability is expressly excluded. Any recommendations made by seller concerning the uses or applications of said product are believed reliable and seller makes no warranty of results to be obtained. If the product does not meet Carthage Mills current published specifications, and the customer gives notice to Carthage Mills before installing the product, then Carthage Mills will replace the product without charge or refund the purchase price.