Product Data Sheet

FX™–600SRF

FX™–600SRF is a specialty woven soil reinforcement geotextile that is manufactured specifically for use in the construction of steepened slopes, embankments and wrapped-face retaining walls. Woven of high tenacity, high molecular weight multifilament polyester yarns in the warp or "reinforcing" direction, FX™–600SRF is resistant to UV degradation and biological and chemical environments normally found in soils.

PROPERTY	SYMBOL	TEST METHOD	DATA	
			METRIC	ENGLISH
☐ **Tensile Properties**			kN/m	lb/ft
MD – Ultimate	T_{ult}	ASTM D 4595	103.5	7091
MD – Ultimate Strain at Failure	ε_{ult}	ASTM D 4595	14.0%	
MD – Tensile Strength @ 5% Strain	$T_{5\%}$	ASTM D 4595	21.6	1482
MD – Creep Reduced Strength	T_l	ASTM D 5262	60.9	4171
☐ **Reduction Factors**				
Creep	RF_{CR}	ASTM D 5262	1.67	
Durability (5 < pH < 8)	RF_D	GRI: GG7 & GG8	1.15	
Installation Damage:				
Soil Type 1 (Gravel): 8mm D_{50}	RF_{ID}	ASTM D 5818	1.34	
Soil Type 2 (Concrete Sand): 0.65mm D_{50}			1.16	
Soil Type 3 (Silty Sand): 0.11mm D_{50}			1.10	
☐ **Design Strength Properties**				
Long Term Design Strength / Allowable Tensile Strength				
T_{ult} / RF for Soil Type 1: Gravel	LTDS/T_{al}	NCMA/FHWA	40.2	2755
T_{ult} / RF for Soil Type 2: Concrete Sand			46.5	3183
T_{ult} / RF for Soil Type 3: Silty Sand			49.0	3357
☐ **Design Interaction Properties**				
Coefficient of Interaction				
Soil Type 1	C_i	ASTM D 6706	0.90	
Soil Type 2				
Soil Type 3				
Coefficient of Direct Sliding				
Soil Type 1	C_{ds}	ASTM D 5321	0.80	
Soil Type 2				
Soil Type 3				
☐ **Scale Correction Factor**	α		1.00	
☐ **Dimensional Properties**	**Units**			
	SI	**US**		
Mass Per Unit Area	g/m^2	oz/yd^2	ASTM D 5261	278.7	8.2
Roll Width	m	ft	Measured	2.1	7.0
Roll Length				91.4	320
Area Per Roll	m^2	yd^2		195.0	249
Estimated Roll Weight	kg	lbs		54.3	131

☐ The values reported are Minimum Average Roll Values (MARV), and are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.

☐ The properties reported above are effective 10/16/03 and are subject to change without notice.

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein. Any implied warranty of fitness for a particular purpose is expressly excluded, and, to the extent that it is contrary to the foregoing sentence, any implied warranty of merchantability is expressly excluded. Any recommendations made by seller concerning the uses or applications of said product are believed reliable and seller makes no warranty of results to be obtained. If the product does not meet Carthage Mills current published specifications, and the customer gives notice to Carthage Mills before installing the product, then Carthage Mills will replace the product without charge or refund the purchase price.

4243 Hunt Road • Cincinnati, Ohio 45242 • 513-794-1600 • **800-543-4430** • 513-794-3434 FAX