



## ■ FX<sup>®</sup>-30HS

Carthage Mills' FX<sup>®</sup>-30HS is a multipurpose nonwoven geotextile of 100% polypropylene staple fibers which are formed into a random network, needlepunched and heatset for dimensional stability. Carthage Mills' FX<sup>®</sup>-30HS is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

PROPERTY	TEST METHOD	DATA	
		METRIC	ENGLISH
<input type="checkbox"/> <b>Mechanical</b>			
Grab Tensile Strength	ASTM D 4632	0.36 kN	80 lbs
Grab Tensile Elongation		50%	
Mullen Burst	ASTM D 3786	896 kPa	130 psi
Trapezoidal Tear	ASTM D 4533	0.11 kN	25 lbs
Puncture	ASTM D 4833	0.13 kN	30 lbs
CBR Puncture	ASTM D 6241	0.93 kN	210 lbs
<input type="checkbox"/> <b>Endurance</b>			
UV Resistance	ASTM D 4355	70% @ 500 hrs	
<input type="checkbox"/> <b>Hydraulics / Filtration</b>			
Permittivity <sup>(1)</sup>	ASTM D 4491	2.00 sec <sup>-1</sup>	
Water Flow Rate <sup>(1)</sup>		6112 lpm/m <sup>2</sup>	150 gpm/ft <sup>2</sup>
Apparent Opening Size (AOS) <sup>(1)</sup>	ASTM D 4751	0.300 mm	50 US Std. Sieve
<input type="checkbox"/> <b>Physical</b>			
Mass Per Unit Area (Typical)	ASTM D 5261	101.7 g/m <sup>2</sup>	3.0 oz/yd <sup>2</sup>
Thickness (Typical)	ASTM D 5199	1.02 mm	40 mils
Standard Roll Sizes / Packaging / Weight	Measured (Typical)	3.81 m x 109.7 m 418 m <sup>2</sup> 56.7 kg	12.5 ft x 360 ft 500 yd <sup>2</sup> 125 lbs
		4.57 m x 109.7 m 501.6 m <sup>2</sup> 66.7 kg	15.0 ft x 360 ft 600 yd <sup>2</sup> 147 lbs

- <sup>(1)</sup> At the time of manufacturing. Handling, storage and shipping may change these properties.
- Unless otherwise stated, all values stated here are Minimum Average Roll Values (MARV), are calculated as the Typical minus two standard deviations and are based on a 97.7% confidence level.
  - The properties reported above are effective 01/05/09 and are subject to change without notice.

Seller makes no warranty, expressed or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specification stated herein. Any implied warranty of fitness for a particular purpose is expressly excluded, and, to the extent that it is contrary to the foregoing sentence, any implied warranty of merchantability is expressly excluded. Any recommendations made by seller concerning the uses or applications of said product are believed reliable and seller makes no warranty of results to be obtained. If the product does not meet Carthage Mills current published specifications, and the customer gives notice to Carthage Mills before installing the product, then Carthage Mills will replace the product without charge or refund the purchase price.